



## **S-30 & S-31 Cove Base Additives**

### **Product Description:**

S-30 & S-31 Cove Base Additives are thickening agents for addition to epoxy mortars and grouts. S-30& S-31 will thicken epoxy mixtures to improve installation appearance of resinous cove base. S-30& S-31 must be used with caution. Wear respiratory protection, rubber type or impervious gloves and goggles when handling S-30& S-31. S-30& S-31 are product specific when mixing with Summitville mortars and grouts. Please indicate when ordering, which Summitville epoxy the S-30 or S-31 order will be used with.

### **Mixing S-30 & S-31:**

For use in Summitville grouts and mortars, use one S-30 or S-31 0.2-pound additive packet for every 3-gallon unit of epoxy grout and/or mortar. Adjust amount added to compensate for atmospheric temperatures. More material may be needed at higher temperatures and less material may be needed at lower temperatures. Summitville recommends mixing S-30 or S-31 into part A of the epoxy a minimum of 8 hours before use. Mixing in at use time will gain the full benefit of the S-30 or S-31.

All vertical work must be completed within 20 minutes of mixing A and B portion of product at 70°F.

### **Shelf Life:**

Do not expose open bags or store bags of S-30 & S-31 in humid conditions. If S-30 is kept dry, S-30 & S-31 shelf life is approximately 5 years. S-30 & S-31 will absorb atmospheric moisture if exposed to any humidity. If an epoxy manufacturer's date is over 1 year, S-30 & S-31 should be added to thicken epoxy for any vertical use.

Once S-30 or S-31 is mixed into part A, Shelf life will be 1 year.

### **Caution:**

Wear respiratory protection, impervious gloves and goggles when handling S-30 & S-31. Summitville recommends avoiding skin contact of S-30 & S-31, as S-30 & S-31 can cause skin irritation to some individuals.

### **Packaging:**

S-30 & S-31 are available in 0.2 and 10 pound bags.